

A Study on Physical & Mechanical Properties of Green Composite

Chanchal Jaiswal¹, Utsav Katiyar², Lokendra Singh³, Shashikant Verma⁴

^{1, 2, 3} Student, ⁴ Assistant Professor

Department of ME, IET, BU, Jhansi, India

Abstract: These days, all researchers are trying to make the research environment safe from fossil fuels. More environmentally friendly materials are urgently needed to alleviate environmental concerns and minimize reliance on fossil fuels. Regarding this issue, everyone is looking for green composites to replace traditional materials. Green composites have a variety of industrial uses and are strong and stiff. This review article discusses the physical & mechanical characterization of green composites, as well as their industrial applications, and how they can be used to replace traditional materials like steel and wood, as well as non-biodegradable polymer composites.

Keyword – Green Composite, Biodegradable Composite, Natural Fiber, Biodegradable Resin, Physical Properties, Mechanical Properties.

I. INTRODUCTION

Because of their enticing material properties, fibre composites stand out among specialists and researchers. Construction, aerospace, automobile, civil, and marine sectors have all made extensive use of them. [1]. Filaments (such as roving, weaved, and thread) supported by a polymer grid have been shown to improve the mechanical characteristics of composites [2]. The two types of strands are man-made and natural fibres (sometimes referred to as synthetic or artificial fibres). Jute, flax, and sisal, for example, have lower densities than synthetic fibres. They have acceptable explicit strength/solidity and break lengths that are somewhat long. Natural-fiber composites (completely biodegradable composites) provide several advantages as compare to synthetic fiber composites, including low price, low weight, abundant availability from sustainable source, eco-friendliness, recyclability, biodegradability, and inexhaustibility. Synthetic fibres like glass, carbon, basalt, aramid, and nylon, are on the other hand, more substantial and grounded than most natural fibres. Synthetic fibre composites have since been used in high-end execution applications such as aeroplane and vehicle manufacturing. Synthetic fibre composites have a low liquefying temperature, are expensive, and are non-degradable, but natural fibre composites (which are made from plants, animals, and minerals) have a high moisture sorption and a poor fiber-grid grip. When making

polymer hybrid composites, using both synthetic and natural fibres together could make the best of both and minimize the worst of both. This section looks at the latest research on half-breed composites made from normal fibres, with a focus on their mechanical properties [3]. A "Composite" is a mixture of at least two distinct materials, at least one of which is reinforcing. This is an extremely broad concept that applies to all composites. Fiber-reinforced composites, which are typically constructed of glass, carbon, & aramid fibres and are reinforced with epoxy, polypropylene, polylactic acid, unsaturated polyester, and other materials [4].

II. GREEN COMPOSITES

Natural fiber-based composites were introduced for the first time in 1908. Green composites are a sort of bio-composites in which a bio-based polymer matrix is reinforced with natural fibres. They are a new subject in polymer science [5]. Green composites are made up of biopolymer matrices or biopolymer reinforced with bio fibres. Green composites are the next generation of sustainable composite materials, and green composite research is gaining traction these days because their next generation composite materials have combined natural fibre and natural resin with developing creation and mass volume use, making the removal of non-biodegradable composites after their useful life has become a significant and costly issue. The majority of these composites are in the

end burned and landfilled. In any case, burning is costly and inefficient. The delivered gases could likewise bring new pollution. Since landfill regions are diminishing and new ecological issues happen along with these customary methods for removal, individuals should be encouraged to track down another compelling method for removal. Also, since composites join two divergent materials [6].

III. RAW MATERIALS FOR GREEN COMPOSITES

Natural fibres: Natural fibres have a number of advantages over traditional reinforcing synthetic fibres (such as carbon and glass), including low density, low cost, inexhaustibility, biodegradability, partitioning ease, high durability, adequate explicit strength, lower energy requirements for handling, and overall accessibility. Natural fibres are those that are derived from natural sources plants and do not require the fibre to be developed or reorganised. Natural fibres are divided into three categories. [7].

Natural fibers are differentiate as the following:

- Plant fibers (lignocellulosic fibers or referred to as cellulosic): Plant fibers are arranged into six kinds including:
- Stem fibers (e.g., flax, paper mulberry, roselle hemp, hemp, isora, jute, kenaf, kudzu, mesta, annoy, okra, ramie, rattan, urena, wisteria)
- Fibers from leaves (e.g., abaca, agave, istle, cantala, caroa, curaua, date palm, fique, Mauritius hemp, piassava, banana, henequen, phormium, sisal)
- Stalk fibers (got from stalks of grain, rice, wheat, maize, oat, and different harvests)
- Cane, grass, and reed fibers (e.g., corn, esparto, albardine, bamboo, bagasse, canary, assault, papyrus, sabia)[8]
- Animal fibers: fiber by and large make out of proteins like collagen, keratin, and fibroin. They are delegated creature fleece or hairs (e.g., goat hair, horse hair, sheep's fleece, alpaca, angora fleece, buffalo, camel, cashmere, mohair, qiviut, yak fleece, and so on), silk fibers (e.g., tussah silk moths, mulberry silk covers), and keratin fiber (e.g., chicken plumes).

Mineral fibres include chrysotile, tremolite, amosite, crocidolite, anthophyllite, and actinolite

asbestos, as well as sinewy brucite and wollastonite [7].

IV. BIODEGRADABLE POLYMER

Bioplastic materials are a class of bio-based, biodegradable, or both materials with a wide range of features and applications. Biodegradable plastics are made from either sustainable or non-sustainable materials, which are completely degraded in the environment by a thermochemical cycle into CO₂, methane, water, biomass, and inorganic compounds that microbes can certainly mineralize [9]. Bio-based polymers, on the other hand, contain natural carbon from sustainable feedstock and are therefore not truly biodegradable. Bio-based polymers can also be made from naturally occurring materials or natural chemicals that have been polymerized into high sub-atomic weight compounds using compound or presumably natural methods. The atomic structure of bio-based materials is similar to that of petrochemical polymers. Most crucially, the chemical structure of a plastic substance determines its biodegradability, not the polymer's carbon wellspring. Bioplastics are a growing, innovative business that provides solutions for a viable plastics economy and plays a critical role in the transition to a bio-based global economy. Regardless of these advantages, the data shows that the global bioplastics business is now being slowed by low oil prices and a lack of governmental support for the bio-based economy. [10].

The breakdown of polymer materials happens by microbial activity, photograph debasement, or compound corruption. Every one of the three techniques are sorted under biodegradation, as the finished results are steady and tracked down in nature. Numerous biopolymers can be unloaded in landfills, manures, or soil. The materials will be separated, provided that the necessary microorganisms are available. Typical soil microscopic organisms and water are regularly adequate, adding to the allure of microbial diminished plastics. Polymers which depend on normally developed materials, for example, starch or flax fiber are defenceless against debasement by microorganisms. The material could conceivably break down additional quickly under vigorous circumstances, dependent upon the plan utilized, and the

microorganisms required. On account of materials where starch is added as an added substance to a regular plastic network, the polymer in touch with the dirt as well as water is gone after by the micro organ [9].

Table 1: different type of natural fiber reinforced with different thermoplastics [11].

No	Natural fiber composites	Density	Tensile strength	Young's modulus
		(g/cc)	(MPa)	(GPa)
1	Kenaf 40 % + PP	1072.00	42.00	6.80
2	Hemp 40 % + PP	1076.00	52.00	6.50
3	Sisal 40 % + PP	1044.00	34.00	5.50
4	Jute 40 % + PP	1036.00	28.00	3.70
5	Bananastem 40% + PLA	712.00	32.00	3.12
6	Coir 40 % + PP	1023.00	10.00	1.30
7	Pineapple 40 % + PS	1526.00	38.00	1.97
8	Bamboo 40 % + HDPE	940.00	21.00	2.75
9	Banana stem 40 % + PP	712.00	39.00	1.05
10	GreenGran NF30	1000.00	41.00	3.90
11	EFB 40 % + PP	875.00	18.00	0.90
12	Flax 36 % + Vinyl ester	1250.00	91.00	9.76

IV. PHYSICAL & MECHANICAL PROPERTIES OF BIODEGRADABLE POLYMER

Because natural fibre has limited mechanical qualities, green composites have lower mechanical properties than GFRP, as previously stated. Hydrophilic and water absorption capabilities, heat deterioration in fibres, poor fiber/lattice grip, and other factors may affect their properties. For the use of natural fibres as reinforcement fibres in composites, the nature of the fiber/network point of interaction is extremely important.

Physical and mechanical techniques such as stretching, heat treatment, plasma treatment, and electric release do not change the synthetic part of the fibres, but they can change the fiber's primary and surface properties, affecting the mechanical properties. Natural fibres that have been treated are inherently incompatible with hydrophobic resins. In this way, coupling specialists in composites examine material strategies such as a difference in fibre surface tension, synthetic coupling, acetylation, and salt treatment to further develop fiber/lattice grip. The increase in cellulose II is typically accompanied by a substantial decrease in natural fibre strength. In this way, I agreed with the outcome of a minor rigidity disaster. When the heap was given to the fibres during salt treatment, the points of the microfibrils, which are spirally placed in the optional mass of the fibre cell, might reduce, enhancing their solidarity. Pressure forming was used to make green composites with fibre volume portions of 60-

70 percent. These findings demonstrated that salt treatment of ramie yarns can definitely increase the effect blockage of green composites.

Mixture composites with stronger protection against natural debasement can have lesser rigidity due to their hydrophobic characteristics and high resistance to thermooxidative corruption. Furthermore, fibre with a high cellulose and hemicellulose content has a high moisture content, which can result in limited interfacial communication between the polymer matrix and the environment. Agglomeration occurs when the amount of fibre in the matrix is high, causing effective pressure to flow between the fibres and matrix. In any event, increasing fibre content at a certain stage might lead to dispersion problems and a reduction in mechanical qualities. Fiber fibres reduce the contact zone between fibres and the matrix in fibre groups, causing strain to be transferred from the network cycle to dispersed strands [7].

Table 2: Chemical Composition of Natural Fibers [12]

Fiber	Lignin (%)	Cellulose (%)	Hemi-cellulose (%)	Pectin (%)	Ash (%)
Kenaf	16-20	30-56	21-23	-----	2-5
Jute	11-25	46-72	12.9-20	0.2	0.5-2
Hemp	3.7-13	57-77	14-22.4	0.9	0.8
Sisal	6-10	46-79	11-25	11	0.6-1
Abaca	6-9	55-62	14-18	-----	3

Table 3: Properties of Polymers [12]

Properties	PLA	PP	PET	Nylon	Cellophane
Density (g/cc)	1.26	0.9	1.5	1.20	1.45
Tensile strength (psi)	15950	27550	29725	36250	13050
Tensile modulus (psi)	478499	347900	551990	264624	594499
Ultimate elongation (%)	159	111	139	124	24

V. APPLICATION

- Bundling has been one of the significant fields of use of green polymers and composites lately.
- Broadly used in different parts of automobile sector [13]
- Science for current medication connected alongside the expansion of green composites is supposed to be a significant subject of compound exercises in the current hundred years.
- The biggest portions for all natural fiber composite applications are the automotive and development.[14]

VI. CONCLUSIONS

In this review paper we have examined about the kind of green composites, handling of green composites and the exploration work happening in

the field of green composites. The emphasis is on working on the handling of green composites in additional conservative manner as the natural substance cost in green composites isn't extremely high. Scientists are involving these green composites in different applications as per their properties. This section looked at mechanical representations of several half and half composites. Half-and-half composites made entirely of natural fibers have a good deal of strength and can be used in a variety of applications. All natural fiber composites have had their physical and mechanical characterization (e.g., flexural, tractable, and influence strength) improved through hybridizations of natural and synthetic fibers in polymer composites. As a result, hybrid polymer composites are promising for better primary applications. When compared to untreated composites, hybrid composites with chemical treatments or fiber modifications have improved mechanical properties. This is due to the superior fiber-matrix holding in treated composites.

REFERENCES

- [1] Clyne T.W., Hull D. (2019) An Introduction to Composite Materials. 3rd ed. Cambridge University Press; Cambridge, UK.
- [2] Pickering K.L., Efendy M.G.A., and Le T.M. (2016) A review of recent developments in natural fibre composites and their mechanical performance. *Compos. Part. A-Appl. S.* 83:98–112. doi: 10.1016/j.compositesa.2015.08.038.
- [3] Nguyen, H., Zatar, W., and Mutsuyoshi, H. (2017). Mechanical properties of hybrid polymer composite. In *Hybrid Polymer Composite Materials: Properties and Characterisation* (pp. 83–113).
- [4] Chandra Kandpal B, Chaurasia R, and Khurana V. (2015) Recent Advances in Green Composites- A Review. *International Journal for Technological Research in Engineering (IJTRE)*. 2(7).
- [5] Reddy N, and Yang Y (2011) Biocomposites developed using water-plasticized wheat gluten as matrix and jute fibers as reinforcement. *Polym Int* 60:711–716.
- [6] Goda K, and Cao Y. (2007) Research and Development of Fully Green Composites Reinforced with Natural Fibers. *Journal of Solid Mechanics and Materials Engineering*. 1(9):1073–84.
- [7] Nguyen H, Zatar W, and Mutsuyoshi H. (2017) Mechanical properties of hybrid polymer composite. In: *Hybrid Polymer Composite Materials: Properties and Characterisation*. Elsevier Inc. p. 83–113.
- [8] Gangil B, Ranakoti L, Verma SK, Singh T, and Kumar S (2020) *Natural and Synthetic Fibers for Hybrid Composites*, Published by Wiley-VCH Verlag GmbH & Co. KGaA <https://doi.org/10.1002/9783527824571.ch1>
- [9] Shahid ul I, Shahid M, Mohammad F (2013) Perspectives for natural product-based agents derived from industrial plants in textile applications—a review. *J Clean Prod* 57:2–18.
- [10] Čolnik M, Hrnčič M K, Škerget M, and Knez Ž. (2020) *Biodegradable Polymers, Current Trends of Research and Their Applications, A Review*. *Chem. Ind. Chem. Eng. Q.* 26 (4) 401–418.
- [11] Jawaid M, Mohd S, Othman S, Alothman Editors Y. (2016) *Green Energy and Technology Green Bio Composites Manufacturing and Properties* [Internet]. Edition: Ist Publisher: Springer-Nature Switzerland, DOI 10.1007/978-3-319-49382-4
- [12] Satyanarayana, K. G., Sukumaran, K., Mukherjee, P. S., Pavithran, C. and Pillai, S. G.K. (1990). Natural Fiber-polymer Composites, *Journal of Cement and Concrete Composites*, 12: 117136.6.
- [13] Verma S K, Gupta A, Patel V K, Gangil B, and Ranikoti L, The potential of natural fibers for automotive sector, Springer, Singapore, (2019) 31-49 https://doi.org/10.1007/978-981-15-0434-1_3
- [14] Georgios K, Silva A, Furtado S. (2016) Applications of Green Composite Materials. In: *Biodegradable Green Composites*. Wiley online library p. 312–37. <https://doi.org/10.1002/9781118911068.ch10>